-15-CLAIMS:

- A intrinsically gel-free, randomly branched polyamide comprising at least units derived from:
 - AB monomers, which monomers have both a carboxylic group (A) and an amine group (B),
 - 2. at least one compound I, being a carboxyulic acid (A_v) having a functionality $v \ge 2$ or an amine (B_w) having a functionality $w \le 2$,
 - 3. at least one compound II, being a carboxylic acid (A_v) having a functionality v ≥ 3 or an amine (B_w) having a functionality w ≥ 3, compound II being a carboxylic acid if compound I is an amine or compound II being an amine if compound I is carboxylic acid if compound I is an amine or compound II being an amine if compound I is a carboxylic acid, characterized in that the amounts of units derived from all carboxylic acids and amines in the polyamide satisfy formula a

$$P \le 1 / [(F_A - 1) (F_B - 1)]$$
 (1)

where

$$P = [\Sigma (n_i f_i)]_x / [\Sigma (n_i f_i)]_Y (2)$$

where $P \le 1$ and either X = A and Y = B, or X = B and Y = A, and

$$F_x = \sum (n_i f_i^2) / \sum (n_i f_i)]$$
 (3)

for, respectively, all carboxylic acids (X=A) and all amines (X=B), where f_i is the functionality of either the carboxylic acid $(f_i=v_i)$ or amine $(f_i=w_i)$, n_i being the number of moles of the carboxylic acid or amine and the summation involving all units derived from carboxylic acids and amines in the polyamide except:

carboxylic acids (A_v) having a functionality v and amines (B_w) having a functionality w, in the following amounts (in μ mol/g of polyamide):

- B₁ (20), B₃ (60) and A₂ (20)
- B₁(10), B₃(60) and A₂(30)
- B₁ (120), B₂ (30) and A₃ (60)
- B₁ (150), B₂ (30) and A₃ (70)
- B₁ (170), B₃ (30), A₂ (60) and A₃ (60).
- The polyamide according to claim 1, the functionality of compound wherein I
 can be chosen from 2, 3, 4, 5 and 6 and the functionality of compound II can
 be chosen from 3, 4, 5 and 6.
- The polyamide according to claim 1, the functionality of wherein compound I
 is 2 and the functionality of compound II is 3.
- The polyamide according to claim 3, wherein at least a unit derived from monofunctional carboxylic acid or amine is present.
- The polyamide according to claim 3, wherein compound I is chosen from the group formed by terephthalic acid and 1, 6-hexa-methylene diamine.
- 6. The polyamide according to claim 3, wherein compound II is chosen from the group formed by 1, 3, 5-tris (caproic acid) melamine, trimesic acid and bis (hexamethylene triamine).
- 7. The polyamide according to claim 1 wherein the AB monomer is an α , ω amino acid and/or a lactam.
- 8. The polyamide according to claim 7, wherein the lactam is c~caprolactam.

- A process for the preparation of a polyamide film, wherein a polyamide
 according to claim 1 is chosen as polyamide.
- A fiber, film, foam or molded article obtained from polyamide according to claim 1.
- 11. A flat film obtained from a polyamide according to claim 1.